

SFM-3.5H-FR

PRODUCT INFORMATION



UL Class “A” fire-rated cap sheet, requiring no additional surface coatings.

OVERVIEW

Bitec SFM-3.5H-FR is a hot asphalt applied, mineral surfaced, modified bitumen waterproofing membrane with a UL Class “A” fire rating, offering additional protection without the need of an additional surface coating. It is composed of carefully selected asphalts and blended with high-quality styrene-butadiene-styrene rubber. SFM-3.5H-FR is reinforced with a high strength fiberglass mat and yields the following performance characteristics:

- Impermeable to water
- Low temperature flexibility
- Thermally stable
- Excellent adhesion
- Resistant to acids and most bases
- Excellent workability
- Longevity
- Mechanical strength
- Deterioration resistance
- Dimensional stability

SFM-3.5H-FR incorporates a smooth and even application of fine slag to prevent blocking of rolls and to provide a smooth, acceptable application surface. SFM-3.5H-FR can be applied by using hot asphalt or by using any Bitec-approved elastomeric cold-process adhesive.* (When using cold adhesives, always follow the specific adhesive manufacturer’s installation specifications.)

Special formulation gives SFM-3.5H-FR a degree of fire resistance to effectively pass UL Class “A” testing without the use of additional surfacings or protective coatings. Systems require a minimum of one UL TYPE G2 base sheet for Class “A” rating, for both combustible and non-combustible decks. Consult UL Building Materials Directory for specific system details, or contact Bitec manager of technical services.

PACKAGING

Palletized units contain 20 rolls of SFM-3.5H-FR waterproofing membrane. Each unit is shrink wrapped in a special polyethylene bag for stability. Bitec recommends that units be single stacked.

APPLICATION

Depending on the type of roof, SFM-3.5H-FR must be fully adhered. Bitec specifications applicable to this product should be consulted to determine which system should be employed. When applying the membrane, the fine slag surface should always be down, facing the roof deck. Prior to application, the membrane should be unrolled completely, aligned, allowed to relax and set before the actual installation of the membrane occurs. The membrane should then be rolled up half way, leaving the other half fully extended. (This will ensure that the membrane will remain aligned during the installation process.)

SFM-3.5H-FR is designed to be applied by conventional methods of hot mopping, using ASTM D312 TYPE III mopping asphalt. ASTM TYPE IV should be used on slopes greater than 3” in 12”. The roofing contractor shall not let the mopping asphalt temperature fall below 450°F, or overheat the asphalt to overcome rapid cooling. Bitec recommends that mopping asphalt EVT requirements be met when heating asphalt. Mopping of base and cap sheet plies shall be done at a rate of 25 lbs./100 ft. sq. in a solid mopping of hot asphalt. It is essential that the asphalt be applied uniformly at a distance not to exceed 4’ in front of the advancing roll surface. A continuous, 1/4” bead of uninterrupted mopping asphalt shall be seen coming from the end and side laps. Seams that are not fully bonded can be repaired by inserting a hot trowel between the affected seam and lightly torching. Upon removal of the hot trowel, pressure should be applied to the top ply, forcing the modified bitumen to flow out the desired distance.

All side and end laps should be a minimum of 4” and 6” respectively. If the membrane is loose laid, an area of 40” each side of the end lap should be fully bonded to the roof surface.

Bitec SBS hot-applied membranes can be installed in hot roofing asphalt or in Bitec-approved cold process adhesives.* Bitec SBS membranes are not recommended for use over coal tar or pitch roofs unless the existing deck is separated from the Bitec membrane by a minimum 1/2” thick, mechanically attached recovery board. Bitec does not allow the use of plastic roofer’s cement with any of its membranes.

As with any roofing project, good roofing practices should always be followed. Consult the Bitec specification and details book for information governing certain systems.

SFM-3.5H-FR

PRODUCT INFORMATION



TOOLS REQUIRED

Tools required to apply Bitec SFM-3.5H-FR waterproofing membrane include: a roofer's kettle, lug bucket, roofer's mop, dial thermometer, spatula or round nose roofer's trowel, a roofer's knife, pair of work gloves, flat-soled shoes and an ABC dry chemical fire extinguisher at the kettle and on the roof.

Before using this product, be certain that all information concerning the installation of this product and safety guidelines pertaining thereto have been read and fully understood. The application of modified bitumen membranes requires the use of explosive gas and molten asphalts, which if mis-handled can and will cause personal injury and/or property damage.

SAFETY

Contractor

It is the contractor's responsibility to observe all fire prevention policies and practices, to train, instruct and warn employees on the use of torching equipment. Follow OSHA and NRCA provisions for fire protection, including but not limited to those listed in OSHA 1910.151, 155, 156, 157, and 1910.1101, which apply to torch application. The contractor should be familiar with NFPA 58 "Standard for the Storage and Handling of Liquefied Petroleum Gas" and any other appropriate publications of the National LP Gas Association.

Fire Department Regulations

The contractor should be familiar with all local fire codes in his area. The contractor is responsible for obtaining all necessary permits or certificates before any work is started.

Personnel

Proper clothing should be worn at all times while installing any modified membrane. Long sleeve shirt, long pants, leather or durable flat-soled shoes and work gloves. Workmen, other than the torch operator, should be no closer than 3' from open flame.

NOTE: The roofing contractor and his employees are the key to success regarding safety. Safety should always be first!

SFM-3.5H-FR

PRODUCT INFORMATION



SFM-3.5H-FR rolls are 3.2' wide and 33.9' long.

Technical Schedule	
APPROVALS	UL (R13231)
SOFTENING POINT (ASTM D-36)	250°F (120°C)
REINFORCEMENT	fiberglass mat
PENETRATION (ASTM D5)	40 dmm @ 25°C
SLIDE (UNI-8202)	<1 mm
WATER TIGHTNESS (CGSB 37-GP-56M)	passed
DYNAMIC PUNCTURE (CGSB 37-GP-56M)	passed
STATIC PUNCTURE (CGSB 37-GP-56M)	passed
TENSILE STRENGTH @ 73.4°F (23°C) (ASTM D-5147)	MD = 74 lbf/in XMD = 59 lbf/in
TENSILE STRENGTH @ 0°F (-17.7°C) (ASTM D-5147)	MD = 152 lbf/in XMD = 115 lbf/in
ELONGATION @ 73.4°F (23°C) (ASTM D-5147)	MD = 6% XMD = 5%
ELONGATION @ 0°F (-17.7°C) (ASTM D-5147)	MD = 5% XMD = 5%
LOW TEMPERATURE FLEXIBILITY (ASTM D-5147)	passed -30°F (-34.4°C)
TEAR STRENGTH @ 73.4°F (23°C) (ASTM D-4073)	MD = 126 lbf/in XMD = 105 lbf/in
THICKNESS	3.5 mm
ROLL WEIGHT, APPROX.	103 lbs
COVERAGE, INSTALLED APPROX.	100 ft ²
TOTAL SURFACE AREA, APPROX.	109.9 ft ²

All Information is given in good faith, but normal tolerances of manufacture and testing will apply. Bitec reserves the right to improve and change its products at any time without prior notice or advice. The use of Bitec products is determined by local conditions and individual requirements of each contract. In consideration of the many factors involved, Bitec cannot be held responsible for the application of its products and for conditions beyond its control. All claims filed against Bitec warranties will be subject to the provisions set forth at the date of warranty issuance, and any addendum thereto. Under no circumstances will Bitec be held liable for any damage, whether personal injury or property damage, which occur during or after the application of the membrane.

Distributed By:

Approvals:



Membrane for Roofing Systems
As to an external fire exposure only
49S8

Member of:



Bitec, Inc.
P.O. Box 497
No. 2 Industrial Park Dr.
Morrilton, AR 72110
Phone: 1-800-535-8597
Fax: 501-354-3019
www.bi-tec.com